



Imerys Diatomita México, S.A. de C.V.

José Antonio Torres No. 400 s/Colonia; General Andrés Figueroa, Jalisco, C.P.45765
Conmutador: (52 326) 434-2000 Fax: (52 326) 434 2067
Oficinas México: (52 55) 5279-9170 Fax: (52 55) 5279-9183

Technical Data

Fibra Cel 4F™

TYPICAL PHYSICAL PROPERTIES

| | |
|----------------------------|------------|
| Color | White |
| Appearance | Powder |
| Description | Filter Aid |
| Permeability, Darcys | 0.15 |
| Wet Density, g/L | 300 |
| lb/ft ³ | 18.7 |
| 150 Mesh Screen Residue, % | 15.0 |
| pH | 10.0 |
| Moisture as shipped, % | 1.0 |

TYPICAL CHEMICAL ANALYSIS, %

| | |
|--------------------------------------|------|
| SiO ₂ | 77.5 |
| Al ₂ O ₃ | 2.0 |
| Fe ₂ O ₃ | 0.9 |
| P ₂ O ₅ | 0.1 |
| TiO ₂ | 0.2 |
| CaO | 0.6 |
| MgO | 0.3 |
| Na ₂ O + K ₂ O | 1.1 |

The typical physical or chemical properties of Imerys Diatomita Mexico products represent average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Typical data shown above are considered accurate and reliable; no guarantee is given or intended.

January / 09 /2012